



## Fluting-125gr (SMF)

( Standard Specification )

| <i>ITEM</i>                       | <i>VALUE</i>   | <i>UNIT</i> | <i>TEST METHOD</i> |
|-----------------------------------|----------------|-------------|--------------------|
| <b>Basis weight</b>               | <b>125 ± 3</b> | gr/m2       | ISO 536            |
| <b>Moisture</b>                   | <b>8.5 ± 2</b> | %           | ISO 287            |
| <b>Breaking length (MD)</b>       | <b>≥ 5.1</b>   | Km          | ISO 1924-2         |
| <b>Tear (CD)</b>                  | <b>≥ 700</b>   | mN          | ISO 1974           |
| <b>Burst</b>                      | <b>≥ 250</b>   | Kpa         | ISO 2758           |
| <b>Crush Medium Test-CMT (MD)</b> | <b>≥ 315</b>   | N           | ISO 7263           |
| <b>Ring Crush Test-RCT (CD)</b>   | <b>≥ 140</b>   | N           | ISO 12192          |



# MAZANDARAN WOOD & PAPER IND.

Email: [marketing@mazpaper.com](mailto:marketing@mazpaper.com)