



Kraftliner (Kraftliner PM1-120gr)

(Standard Specification)

<i>ITEM</i>	<i>VALUE</i>	<i>UNIT</i>	<i>TEST METHOD</i>
Basis weight	120 ± 2.5	gr/m2	ISO 536
Moisture	8.5 ± 1.5	%	ISO 287
Breaking length (MD)	≥ 6.5	Km	ISO 1924-2
Tear (CD)	≥ 1000	mN	ISO 1974
Burst	≥ 300	Kpa	ISO 2758
Roughness Top	≤ 9.5	µm	ISO 8791-4
Cobb 60	33 ± 5	gr/m2	ISO 535



MAZANDARAN WOOD & PAPER IND.

Email: marketing@mazpaper.com