



## Kraftliner ( Kraftliner PM1-70gr)

( Standard Specification )

<i>ITEM</i>		<i>VALUE</i>	<i>UNIT</i>	<i>TEST METHOD</i>
<b>Basis weight</b>		<b>70 ± 2</b>	gr/m2	ISO 536
<b>Moisture</b>		<b>8.5 ± 1.5</b>	%	ISO 287
<b>Breaking length (MD)</b>		<b>≥ 6</b>	Km	ISO 1924-2
<b>Tear (CD)</b>		<b>≥ 480</b>	mN	ISO 1974
<b>Burst</b>		<b>≥ 185</b>	Kpa	ISO 2758
<b>Roughness</b>	<b>Top</b>	<b>≤ 7</b>	µm	ISO 8791-4
<b>Cobb 60</b>		<b>33 ± 5</b>	gr/m2	ISO 535



# MAZANDARAN WOOD & PAPER IND.

Email: [marketing@mazpaper.com](mailto:marketing@mazpaper.com)