



Printing & Writing -50gr

(Standard Specification)

<i>ITEM</i>	<i>VALUE</i>	<i>UNIT</i>	<i>TEST METHOD</i>
Basis weight	50 ± 1	gr/m ²	ISO 536
Moisture	8 ± 1	%	ISO 287
Caliper	65 ± 15	µm	ISO 534
Breaking length (MD)	≥ 4.5	Km	ISO 1924-2
Tear (CD)	≥ 300	mN	ISO 1974
Burst	≥ 85	Kpa	ISO 2758
Brightness	≥ 70	%	ISO 2470
Opacity	≥ 80	%	ISO 2471
Cobb 60	25 ± 5	gr/m ²	ISO 535



MAZANDARAN WOOD & PAPER IND.

Email: marketing@mazpaper.com